

**BGTEX-H25**

BGTEX-H25 is styrene acrylic copolymer dispersion with the following inherited properties: self crosslinking and Alkyl Phenol ethoxylated free surfactant. **BGTEX-H25** designed for use as a binder for hard textile printing while keeping good wet and dry scrub resistance.

BGTEX-H25 Typical Properties :

Solids Content	50±1%
Viscosity (Brookfield, LVT 1/60, 25°C)	20-100 cps
PH	4.5- 6.5
Specific Gravity at 25°C	1.04
Surfactant Type	Anionic/ Nonionic
Minimum Film Formation Temperature	40°C

Film Properties :

BGTEX-H25 forms a colorless, hard film. Due to the monomers selection, the film exhibit Inhibition of water penetration and good wear resistance.

Packaging :

200-kilo lacquer lined metal drums with polyethylene inner liner, 1-ton polyethylene container.

Storage :

BGTEX-H25 can be stored in original containers it is supplied in. Store in shade and protect from freezing.

Further Information about safe handling of this product can be found in the publication, "B.G. Polymers Safety Data Sheet".

All the information included in this data sheet is correct and is presented to the best of our knowledge and experience without warranty. Information on the use of our products should be adapted to local conditions. B.G Technologies cannot accept responsibility or liability for any damage, loss or patent infringements from the use of this information.